

# Natural NR/SBR

## SPECIFICATION SHEET

|                              |                     |            |
|------------------------------|---------------------|------------|
| Grade                        | N43                 |            |
| Colour                       | PINK                |            |
| Elastomer                    | NATURAL             |            |
| Quality                      | HIGH GRADE ABRASION |            |
| Hardness Shore A $\pm 5$     | 38°                 | ISO 7619-1 |
| SG (g/cm <sup>2</sup> )      | 0.98                | ISO 2781   |
| Tensile (N/mm <sup>2</sup> ) | 20                  | ISO 37     |
| Elongation %                 | 780                 | ISO 37     |
| Compression %                | 20%                 | ISO 37     |
| Tear Strength                | 27                  | ISO 34-1   |
| Abrasion mm <sup>3</sup>     | 80                  | ISO 37     |
| Temperature (°C) from        | -20                 |            |
| Temperature (°C) to          | 70                  |            |

### Roll Tolerances

|                   |        |              |
|-------------------|--------|--------------|
| Width tolerance:  | +/- 2% | ISO 3302 SW1 |
| Length tolerance: | +/- 2% | ISO 3302 SW1 |

### Thicknesses available

|             |            |
|-------------|------------|
| 1mm to 6mm  | 1.4m x 10m |
| 8mm to 25mm | 1.4m x 5m  |

### Thickness

|            |            |
|------------|------------|
| 0.5– 1mm   | +/- 0.2mm  |
| 1.5mm –3mm | +/- 0.3mm  |
| 4mm—5mm    | +/- 0.4mm  |
| 6mm        | +/- 0.5mm  |
| 8mm        | +/- 0.7mm  |
| 10mm—15mm  | +/- 1mm    |
| 20mm       | +/- 1.4mm  |
| 25mm       | +/- 1.75mm |

32mm, 38mm, 1m x 1m  
40mm and  
52mm

● Items listed above usually ex stock.

Other thicknesses and sizes available, please contact sales office for your requirements

### QUALITY ASSURED PRODUCTS WITH FULL TRACEABILITY

Care should be taken in selecting the most suitable quality for each application.  
Advice is available but final responsibility remains with the customer.