

Neoprene CR/SBR

SPECIFICATION SHEET

Grade	C26	
Colour	BLACK	
Elastomer	CR/SBR	
Quality	BS2752-C60	
Hardness Shore A ± 5	60°	ASTM D2240
SG (g/cm ²)	1.30	
Tensile (N/mm ²)	13	ASTM D412
Elongation %	250	ASTM D412
Compression %	25	ISO 37
Tear Strength	20	D624 DIE C
Abrasion mm ³		
Temperature (°C) from	-35	
Temperature (°C) to	120	

Roll Tolerances

Width tolerance:	+/- 2%	ISO 3302 SW1
Length tolerance:	+/- 2%	ISO 3302 SW1

Thicknesses available

1mm to 6mm 1.4m x10m

8mm to 25mm 1.4m x 5m

32mm, 38mm, 40mm and 52mm 1m x 1m

Thickness

0.5– 2mm	+/- 0.2mm
2mm –4mm	+/- 0.3mm
5mm –6mm	+/- 0.4mm
6mm-10mm	+/- 0.5mm
10mm-15mm	+/- 0.8mm
20mm	+/- 1mm
25mm	+/- 1.25mm
30MM	+/- 1.5mm

● Items listed above usually ex stock.

10mm thick available in 1.4m x 5m and 1.4m x 10m
Other thicknesses and sizes available, please contact sales office for your requirements

QUALITY ASSURED PRODUCTS WITH FULL TRACEABILITY

Care should be taken in selecting the most suitable quality for each application.
Advice is available but final responsibility remains with the customer.